

Technical Data Sheet



Conventional Roadrunner



Characteristics:

- ❖ Good bead adhesion
- ❖ Spreading rate of 300 linear feet per gallon of 4-inch line
- ❖ Can be applied with standard striping equipment
- ❖ Easy clean-up with Mineral Spirits or VM&P Naphtha

Cautions:

- ❖ May bleed on fresh asphalt or sealcoated surfaces – See “Application Procedures – Solvent Based Paint”
- ❖ This paint may lift improperly aged or inferior asphalt pavements
- ❖ Keep away from all heat sources – **FLAMMABLE**

Specifications

Viscosity:	80 – 90 Krebs Units	Total Solids:	75 % Minimum
Weight per Gallon:	12.50 Minimum	Solvent Type:	VM&P Naphtha
Shelf Life:	9 Months Minimum Properly Stored	Vehicle Type:	Alkyd Resin
Dry to NPU:	15 to 30 Minutes track free at 15 mils wet		