

Technical Data Sheet



Florida FD WB 2 Min

FFW-254, FFY-255, FFB-257, FFW-256



Characteristics:

- ❖ Low VOC (150g/L Max.)
- ❖ Dry through in 2 hours maximum even at high humidity
- ❖ Can be used on highways or parking lots
- ❖ Non-flammable
- ❖ Non-bleeding
- ❖ Spreading rate of 300 linear feet per gallon of 4-inch line
- ❖ 100% Acrylic Binder
- ❖ Easy clean-up with soap and water

Cautions:

- ❖ **CANNOT** be used in galvanized, brass, aluminum, or steel equipment; Recommend stainless steel or plastic components
- ❖ Keep from freezing
- ❖ Addition of water or other soluble solvents will adversely affect dry time
- ❖ All equipment should be cleaned before paint dries

Specifications

Viscosity: 80 – 100 Krebs Units	Total Solids: 75 % Minimum
Weight per Gallon: 13.5 +/- 1.4#/Gal	Pigment%: 57 % Min.
Ph: 9.5 Min.	TiO² Content: FFW-254 – 1.5#/Gal Min.
Grind: 2 to 3	FFW-256 – 1.0#/Gal Min.